



TECHNICAL DATA SHEET Version: 002 Update : August, 2018

CONSOL 82 LP

DESCRIPTION

CONSOL 82 LP is a solvent-free, thixotropic, 2component structural epoxy resin adhesive. Perfect bond for new concrete surface to old concrete.

RECOMENDED FOR

CONSOL 82 LP is used to bond fresh, plastic concrete, to hardened concrete and steel. Structural adhesive for oncrete, mansory, metal, wood etc.

BENEFITS

CONSOL 82 LP is a deeply penetrative with high adhesive qualities. Other benefits are:

- Long pot life
- High strength bonding
- Excellent adhesion to most structural materials
- High early and final strength
- Insensitive to moisture before, during and after cure
- High effective, even on damps surfaces
- Can be applied with roller

PRODUCT DATA

Coverage $0.3 - 0.8 \text{ kg/m}^2$ depending on substrate condition

Colour Light grey

Packaging 5 kg set

Shelf Life 12 months when unopened and stored correctly

TECHNICAL DATA

Mix Density ~1.5 kg/Litre

Pot Life Approx. 120 minutes

Mixing Ratio Comp A : B = 2 : 1 parts by weight and volume **Compressive strength**

> 40 MPa (7 days) > 45 MPa (28 days)

Flexural strength > 40 MPa (28 days)

Tensile strength > 17.5 MPa (28 days)

Bond strength To Concrete > 2 MPa (28 days)

INSTRUCTION FOR USE

Surface Preparation

Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compound, impregnation, waxes, foreign particles, disintegrated materials.

Preparation work

Concrete: Sandblast or use other approved mechanical methods. : white material finish Steel

Mixing

Pre-Mix each component. Proportion 2 part Component A to 1 part Component B into clean pail. Mix thoroughly 3 minutes with a paddle on low speed until uniform in color.

Application

To bond fresh concrete to hardened concrete. Apply by brush, roller, or broom, place fresh concrete while CONSOL 82 LP is still tacky.

HANDLING PRECAUTIONS

- Avoids contact with skin and eyes
- Wear protective gloves and eye protection during work
- · If skin contact occurs, wash skin thoroughly
- If in eyes, hold eyes open, flood with warm water and seek medical attention without delay.



HEAD OFFICE PERTOKOAN WADUNG ASRI PERMAI Blok B 8 Jl. Raya Wadung Asri 46-48 Waru - Sidoarjo Telp. 031 8661122 - Fax. 031 8661122

BRANCH OFFICE : GUDANG TAMBUN CITY JI. Sultan Hasanudin 263-265 Tambun City Blok E No. 2 Tambun Selatan - Bekasi, Telp. 021 89510184

FACTORY Kompleks Industri dan Pergudangan Golden Blok B16-17 Jl. Industri II Tambak Sawah, Waru Sidoarjo 61256