



TECHNICAL DATA SHEET Version : 008 Update : October, 2021

CONSOL SG

Water Reducing and Set Retarding Concrete Admixture

DESCRIPTION

CONSOL SG is a liquid concrete plasticizer and water reducing agent with set retarding effect.

CONSOL SG complies with ASTM C494/C494M-19 Type D.

RECOMENDED FOR

CONSOL SG is used as a general purpose admixture when the placing conditions. For high quality concrete are more demanding such as:

- Elevated temperature
- Fair faced concrete
- Pumped concrete
- Ready-mix concrete
- Area where large volumes must be placed at one time
- High mechanical strengths are required

BENEFITS

CONSOL SG provides the following properties:

- Increased setting time in hot weather
- Accelerated hardening after setting
- Improved workability without increase water content
- · Reduced water without loss of workability
- Increased strengths
- Reduced shrinkage and creep
- Long lasting control of slump loss
- Better surface finish
- Chloride free does not attack reinforcement

PRODUCT DATA

Form

Liquid

Colour Brownish

Packaging 200 litres sealed drum 1000 litres IBC's or tanker delivery on request Storage

Dry, cool, shaded place. Protect from direct sunlight and frost.

Shelf Life

CONSOL SG can be stored for 12 months if stored as recommend in unopened original containers

TECHNICAL DATA

Type Polyhydroxy Carbon Salts

Specific Gravity 1.15 ± 0.02 kg/L

TINSTRUCTION FOR USE

Dosage

0.15% - 0.50% by weight of cement

The dosage rate can be increased to 0.50% to overcome difficulties in quality of cement and aggregates, high temperature and difficult placing conditions. It is advisable to carry out trial mixes to establish the exact dosage rate required. **CONSOL SG** is compatible with all types of Portland cement including S.R.C.

Dispensing

CONSOL SG should be dispensed directly into the mixing water prior to its addition to the aggregates. When accidental overdosing occurs, **CONSOL SG** does not entrain excessive amounts of air, however the set retarding effect increases. During this period, the concrete must be kept moist in order to prevent premature drying out.

HANDLING PRECAUTIONS

- Avoids contact with skin and eyes
- Wear protective gloves and eye protection during work
- If skin contact occurs, wash skin thoroughly
- If in eyes, hold eyes open, flood with warm water and seek medical attention without delay.

For detail health, safety and environmental recommendations, please consult and follow all instruction on the Material Safety Data Sheet.



PERTOKOAN WADUNG ASRI PERMAI Blok B 8 J. Raya Wadung Asri 46-48 Waru - Sidoarjo Telp. 031 8661122 - Fax. 031 8661122

 BRANCH OFFICE : GUDANG TAMBUN CITY
JI. Sultan Hasanudin 263-265 Tambun City Blok E No. 2 Tambun Selatan - Bekasi, Telp. 021 89510184

FACTORY

Kompleks Industri dan Pergudangan Golden Blok B16-17 JI. Industri II Tambak Sawah, Waru Sidoarjo 61256